

Copaquire Drill Program - Final Results CQ-70 - CQ-99

Hole #	From (m)	To (m)		Width (m)	% Mo	% Cu	g/t Re	CuEq%*
CQ70	0.0	250.0	EOH	250.0	0.029	0.16	0.11	0.43
including	4.0	30.0		26.0	0.003	0.39	0.03	0.42
including	104.0	250.0		146.0	0.043	0.16	0.16	0.54
CQ71	12.0	252.0		240.0	0.024	0.09	0.05	0.31
CQ72	0.0	578.2	EOH	578.2	0.040	0.07	0.10	0.43
including	480.0	578.2		98.2	0.090	0.05	0.27	0.86
CQ73	0.0	418.3	EOH	418.3	0.024	0.11	0.05	0.32
including	146.0	212.0		66.0	0.061	0.14	0.11	0.68
including	342.0	354.0		12.0	0.079	0.07	0.10	0.78
CQ74	110.0	478.9	EOH	368.9	0.004	0.08	0.00	0.12
CQ75	7.9	556.4	EOH	548.6	0.033	0.07	0.05	0.37
CQ76	0.0	363.0	EOH	363.0	0.017	0.11	0.05	0.26
including	158.0	220.0		62.0	0.025	0.06	0.06	0.29
including	220.0	236.0		16.0	0.056	0.04	0.10	0.55
CQ77	0.0	326.8	EOH	326.8	0.003	0.08	0.03	0.11
CQ78	4.3	352.6	EOH	348.3	0.004	0.06	0.00	0.10
CQ79	0.0	370.0	EOH	370.0	0.020	0.12	0.08	0.30
including	72.0	258.0		186.0	0.028	0.12	0.12	0.37
CQ80	0.0	210.0		210.0	0.016	0.10	0.03	0.24
	256.0	376.8		120.8	0.013	0.05	0.02	0.17
CQ81	138.0	364.0		226.0	0.025	0.16	0.08	0.38
including	138.0	196.0		58.0	0.039	0.17	0.17	0.52
CQ82	0.0	326.0		no assays				
CQ82	326.0	483.0	EOH	157.0	0.020	0.07	0.03	0.25
including	438.0	483.0		45.0	0.033	0.09	0.05	0.39
	0.0							
CQ83	5.0	318.7	EOH	313.8	0.021	0.13	0.04	0.32
including	5.0	68.0		63.1	0.052	0.16	0.08	0.63
CQ84	0.0	634.8	EOH	634.8	0.042	0.15	0.09	0.53
including	318.0	576.0		258.0	0.057	0.06	0.10	0.58
including	528.0	566.0		38.0	0.075	0.05	0.13	0.73
including	122.0	282.0		160.0	0.034	0.31	0.09	0.62
CQ85	4.6	510.0	EOH	505.5	0.031	0.17	0.05	0.45
including	406.0	432.0		26.0	0.077	0.25	0.09	0.94
CQ86	6.0	336.0		330.0	0.026	0.10	0.05	0.34
including	6.0	50.0		44.0	0.052	0.13	0.09	0.60

Hole #	From (m)	To (m)		Width (m)	% Mo	% Cu	g/t Re	CuEq%*
CQ87	0.0	177.0	EOH	177.0	0.017	0.24	0.03	0.40
including	58.0	114.0		56.0	0.012	0.40	0.03	0.51
CQ88	0.0	421.5	EOH	421.5	0.037	0.11	0.07	0.44
including	40.0	148.0		108.0	0.072	0.10	0.15	0.75
CQ89	0.0	96.5	EOH	96.5	0.012	0.11	0.02	0.22
including	80.0	96.5		16.5	0.036	0.34	0.08	0.66
CQ90	0.0	472.0	EOH	472.0	0.033	0.12	0.06	0.42
including	0.0	140.0		140.0	0.046	0.14	0.08	0.55
including	28.0	48.0		20.0	0.049	0.40	0.09	0.85
CQ91	0.0	228.0	EOH	228.0	0.023	0.16	0.04	0.36
including	142.0	176.0		34.0	0.045	0.32	0.06	0.73
CQ92	0.0	332.0	EOH	332.0	0.027	0.13	0.07	0.37
including	140.0	168.0		28.0	0.050	0.30	0.14	0.75
including	300.0	326.0		26.0	0.054	0.09	0.09	0.57
CQ93	92.0	119.0		27.0	0.004	0.39	0.01	0.42
CQ94	148.0	180.0		32.0	0.052	0.26	0.03	0.73
including	54.0	92.0		38.0	0.002	0.30	0.00	0.32
CQ95	0.0	247.0	EOH	247.0	0.018	0.10	0.04	0.26
including	4.0	12.0		8.0	0.002	0.86	0.01	0.87
CQ96	0.0	42.7	EOH	42.7	0.008	0.10	0.03	0.17
CQ97	58.0	122.0	EOH	64.0	0.009	0.356	0.03	0.44
CQ98	0.0	246.2	EOH	246.2	0.009	0.375	0.02	0.46
including	50.0	162.0		112.0	0.013	0.572	0.02	0.69
including	50.0	76.0		26.0	0.022	0.743	0.02	0.94
CQ99	0.0	32.8	EOH	32.8	0.009	0.03	0.01	0.11
		hole abandoned due to drill breakdown						

*Note: Copper Equivalent herein is based upon metal prices of US\$3.67/lb Cu, US\$33.50/lb Mo. (June 8, 2008) The formula used is Cu Equivalent % = Cu % + (Mo% x Price per pound for Mo/Price per pound for Cu.

Re has not been used in copper equivalent calculation